

Quality Test Report

ORIGINAL

Test Report No. TW-2060018A

1 / 2

Applicant: Ming Fong Technology Co., Ltd.
No. 13, Zhongshan RD., Tucheng Dist.,
New Taipei City 23680, Taiwan

December 11, 2020

Test results to the sample submitted are as follows.

BOKEN QUALITY EVALUATION INSTITUTE

BOKEN

**Taiwan Testing Center
SGS Taiwan Ltd.**

Date of reception: June 30, 2020

Item Name/Item number: :Tempered Glass coated with
JM nanocomposite material

Quantity: 2

31, Wu Chyuan Road, New Taipei Industrial Park,

Wu Ku Dist., New Taipei City 24886, Taiwan

TEL.+886-2-2299-3279/FAX.+886-2-2299-9630

[Test Item] A method specified by the applicant (Determination of antiviral activity)

[Reference standard] ISO21702, JIS R 1702

[Test Method]

Virus solution prepared so that viable account in the MEM medium is about 10^8 PFU/mL or more was diluted 10 times with sterile purified water. Used it as test virus solution.

Inoculated 0.4 mL of the test virus solution on each 5 cm square specimen placed, covered them with 4 cm cover film and irradiated the light under black light for 4 h.

After 4 h light-irradiation, put them into stomacher bags, added 10 mL of the washing-out solution, kneaded sufficiently and washed the virus out.

Measured the virus infectivity titer in the wash-out solution and calculated the common logarithm value of the infectivity titer per cm^2 of test specimen. Used "Tempered Glass (Blank)" as a comparison control, and carried out the measurements after 4 h and immediately after inoculation.

Type of the light source: fluorescent blacklight lamp 20 W x 2 (TOSHIBA FL20S BLB)

Integrating UV light meter: Hamamatsu Photonics K.K., C10427, H10428

Irradiation condition: $0.25 \text{ mW/cm}^2 \cdot 4 \text{ h}$ ($25 \pm 5 \text{ }^\circ\text{C}$)

Type of the cover film: film sheet for overhead projector

Type of the glass for moisture retention: borosilicate glass

Wash-out solution: SCDLP medium

Measurement method of the virus infectivity titer: Plaque assay

[Test virus] Influenza A virus (H1N1): ATCC VR-1469

Notice - This test result is applied to the submitted sample, not to the lot.

Unauthorized reproduction, in whole or in part, is strictly prohibited.



Quality Test Report

Test Report No. TW-2060018A

2 / 2

[Test Result]

Concentration of the test virus: 2.5×10^7 PFU/mL

Name of the sample	Common logarithm value of infectivity titer	Antiviral activity value
Tempered Glass (Blank), immediately after inoculation [U ₀]	5.83	_____
Tempered Glass (Blank), after 4 h [U _t]	5.06	_____
Tempered Glass coated with JM nanocomposite material (JM-TTA01) [A _t]	2.56	2.5

* Calculation of antiviral activity value in ISO21702:2019.


$$\text{Antiviral activity value} = U_t - A_t$$

* Tested by Boken Osaka laboratory.

BOKEN QUALITY EVALUATION INSTITUTE

Taiwan Testing Center

Supervised by



Notice – This test result is applied to the submitted sample, not to the lot.
Unauthorized reproduction, in whole or in part, is strictly prohibited.

