

Quality Test Report

ORIGINAL

Test Report No. TW-2060019A

1 / 2

Applicant: Ming Fong Technology Co.,Ltd.
No.13, Zhongshan RD., Tucheng Dist.,
New Taipei City 23680, Taiwan

December 11 , 2020

BOKEN QUALITY EVALUATION INSTITUTE

BOKEN

Taiwan Testing Center
SGS Taiwan Ltd.

Test results to the sample submitted are as follows.

Date of reception: June 30 , 2020

Item Name/Item number: : Thermoplastic Elastomer
coated with JM nanocomposite material

Quantity: 2

31, Wu Chyuan Road, New Taipei Industrial Park,

Wu Ku Dist., New Taipei City 24886, Taiwan

TEL.+886-2-2299-3279/FAX.+886-2-2299-9630

[Test Item] A method specified by the applicant (Determination of antiviral activity)

[Reference standard] ISO21702, JIS R 1702

[Test Method]

Virus solution prepared so that viable account in the MEM medium is about 10^8 PFU/mL or more was diluted 10 times with sterile purified water. Used it as test virus solution.

Inoculated 0.4 mL of the test virus solution on each 5 cm square specimen placed, covered them with 4 cm cover film and irradiated the light under black light for 4 h.

After 4 h light-irradiation, put them into stomacher bags, added 10 mL of the washing-out solution, kneaded sufficiently and washed the virus out.

Measured the virus infectivity titer in the wash-out solution and calculated the common logarithm value of the infectivity titer per cm^2 of test specimen. Used "Thermoplastic Elastomer (Blank)" as a comparison control, and carried out the measurements after 4 h and immediately after inoculation.

Type of the light source: fluorescent blacklight lamp 20 W x 2 (TOSHIBA FL20S BLB)

Integrating UV light meter: Hamamatsu Photonics K.K., C10427, H10428

Irradiation condition: $0.25 \text{ mW/cm}^2 \cdot 4 \text{ h}$ ($25 \pm 5 \text{ }^\circ\text{C}$)

Type of the cover film: film sheet for overhead projector

Type of the glass for moisture retention: borosilicate glass

Wash-out solution: SCDLP medium

Measurement method of the virus infectivity titer: Plaque assay

[Test virus] Influenza A virus (H1N1): ATCC VR-1469

Notice - This test result is applied to the submitted sample, not to the lot.

Unauthorized reproduction, in whole or in part, is strictly prohibited.



Quality Test Report

Test Report No. TW-2060019A

2 / 2

[Test Result]

Concentration of the test virus: 2.5×10^7 PFU/mL

Name of the sample	Common logarithm value of infectivity titer	Antiviral activity value
Thermoplastic Elastomer (Blank), immediately after inoculation [U ₀]	5.85	_____
Thermoplastic Elastomer (Blank), after 4 h [U _t]	5.30	_____
Thermoplastic Elastomer coated with JM nanocomposite material (JM-TTA01) Sample D [A _t]	2.98	2.3

* Calculation of antiviral activity value in ISO21702:2019.


$$\text{Antiviral activity value} = U_t - A_t$$

* Tested by Boken Osaka laboratory.

BOKEN QUALITY EVALUATION INSTITUTE

Taiwan Testing Center

Supervised by



Notice - This test result is applied to the submitted sample, not to the lot.
Unauthorized reproduction, in whole or in part, is strictly prohibited.

